

Technical data sheet 200715	Flux Cored Welding Wire HARDFACE 19 9 6-O	
---	---	---

CLASSIFICATION

EN 14700 : T Fe10

DESCRIPTION

- Tubular wire for self shielded metal arc hardfacing
- Austenitic stainless weld deposit
- Good impact, cavitation and corrosion resistance
- The weld deposit work hardens to different degrees depending on amount of impact
- Resists scaling up to 850°C, good resistance to thermal shocks

APPLICATIONS

- HARDFACE 19 9 6-O is mainly used to rebuild components exposed to high impact and corrosion
- Sub-layer before hardfacing, particularly on manganese steels and “hard to weld” steels

Examples

Steel mill rolls, metallurgical plant guides, tram and train rails and crossings, high speed forming rolls

TYPICAL ALL-WELD METAL ANALYSIS

C	Mn	Si	Cr	Ni
0.1	6	0.5	19	9

Structure: austenite

TYPICAL ALL-WELD METAL MECHANICAL PROPERTIES

Hardness – 3-layer deposit: As welded 180 HB
Work hardened 47 HRC

CONDITIONS OF USE

Current type	Protection
DC+	Self shielded

OPERATING CONDITIONS

Diameter [mm]	Current [A]		Voltage [V]		Stick-out [mm]	
	Range	Optimum	Range	Optimum	Range	Optimum
1.2	100 - 300	250	21 - 35	28	25 - 50	25
1.6	150 - 350	270	24 - 35	28	25 - 50	25
2.0	200 - 400	300	26 - 35	28	25 - 50	35
2.4	250 - 450	350	26 - 35	28	25 - 50	40
2.8	250 - 450	400	28 - 35	30	25 - 50	40

Recovery: 90 %

WELDING POSITIONS

Flat, half up, half down

PACKAGING

Diameter	≤ 2.4 mm	≥ 2.4 mm	
Standard packaging	EN ISO 544 : BS 300 spool	Coil	Drum
Weight	15 kg	25 kg	Up to 330 kg

Other packaging: please consult us

Welding products and techniques evolve constantly. All descriptions, illustrations and properties given in this data sheet are subject to change without notice and can only be considered as suitable for general guidance. This document is intended to help the user make the correct choice of product. It is his responsibility to assess its suitability for his intended application.